

DX1062

2K PRODUCTIVE VOC SURFACER

Description

Extremely fast drying, 2-component VOC compliant surfacer.
Colour: medium grey.
Composition based on functional acrylic copolymer.

Products

DX1062	2K HS Productive Primer
DX1020	HS Activator
DX1024	HS Activator Fast
DX32	Thinner Fast
DX34	Standard Thinner

Properties

- Easy to apply, smooth flow.
- Very high productive surfacer: easy wet and dry sandability after 1 hr air dry, very short flash time between coats.
- Very easy to sand, many days after application.
- Superb filling.
- Can be coated with basecoat or 2K topcoat.
- VOC compliant, conform with directive 2004/42/EC.









Substrates

- OEM finishes.
- Cured repair finishes.
- Sanded putties.
- Primed steel, zinc galvanised steel and aluminium.
- DUXONE® 1K Wash Primer Filler DX1061.

DX1062

2K PRODUCTIVE VOC SURFACER

PRODUCT PREPARATION

	Mixing ratio DX1062 DX1020/DX1024 DX32/DX34	Standard (DX1020)		Fast (DX1024)	
		Volume	Weight	Volume	Weight
		4	100	4	100
		1	18	1	18
		5-10%	4-8	5-10%	4-8
	VOC 540 g/l				
	Pot life at 20°C DX1020 DX1024	1 hr 1 hr			
	Spray viscosity at 20°C DIN 4 FORD 4 AFNOR 4	22-25 s 22-27 s 24-31 s			
	Spray equipment Conventional guns Gravity feed Suction feed Pressure feed Compliant guns (HVLP/HTE) Gravity feed Suction feed Pressure feed	Fluid tip	Distance	Pressure	
		1.4-1.8 mm 1.6-1.8 mm 1.0-1.2 mm	20-25 cm 20-25 cm 20-25 cm	3-4 bar 3-4 bar 3-4 bar	
		1.4-1.7 mm 1.6-1.8 mm 1.0-1.2 mm	15-20 cm 15-20 cm 15-20 cm	According to supplier's specifications	
	Number of coats	1-3			
	Flash time	Between coats till flat. 10 min before bake.			
	DFT	50-100 µ			
	Dry to sand at 15°C at 20°C at 40°C at 60°C	DX1020		DX1024	
		2-3 hr 1-2 hr 30-40 min 30 min	1-2 hr 1 hr 30 min 20 min		
	IR drying*	Distance Half power Full power	80 cm 5 min 10-15 min		
* Guideline for short/medium wave IR equipment.					
This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.					

DX1062

2K PRODUCTIVE VOC SURFACER

RECOMMENDED USE

Surface preparation

- Before applying DX1062, clean the surface, sand and degrease properly.

Equipment cleaning

Use a correct solventborne gunwash.

Remarks

- Do not use activated DX1062 beyond the pot life nor reduce it further to get viscosity down again.
- If DX1062 is applied over thermoplastic acrylic finishes, complete panel or overall car has to be treated. Spot repairing or sand throughs of the primer can result in spot marking or lifting when applying a basecoat.
- Do NOT exceed recommended film thickness to avoid film defects, poor film through cure and poor adhesion.
- Respect mixing ratios, drying times, spray pressure and DFT to avoid poor sandability and paperfilling.
- Activated material should not be returned to original can of non-activated material.
- Close can of activator tightly immediately after use, as this product will react with humid air and water and lose its hardening effect.
- Material has to be at room temperature (18-25°C) before use.

DX1062

2K PRODUCTIVE VOC SURFACER

RECOMMENDED USE (con'd)

Product data

Package viscosity:	2500-3000 cp (at 5 rpm) 900-1200 cp (at 20 rpm)
Theoretical coverage	4.8 – 5.0 m ² /l at 80 μ DFT - ready-to-spray
Directive 2004/42/EC:	The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

Products	Packages (l)	Shelf life at 20°C (year)	Density (kg/l)
DX1062	1	2	1.330
DX1020	0.5	3	1.007
DX1024	0.5	3	1.007
DX32	1 - 5	5	0.874
DX34	1 - 5	5	0.903

Safety

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.